

Safety Zone

7 Mil Clear

MECHANICAL PROPERTIES

| | |
|----------------------------------|--------------------|
| Thickness | 7 mil |
| Tensile Strength at Break | 26,000 PSI |
| Break Strength | 180 lb/inch |
| Elongation at Break | 140 % |
| Peel Strength | 7 lb/inch |



OPTICAL & SOLAR PROPERTIES

| | |
|---------------------------------------|-------------|
| Visible Light Transmitted | 85 % |
| Visible Light Reflected | 11 % |
| Ultra Violet Block | 90 % |
| Total Solar Energy Reflected | 9 % |
| Total Solar Energy Transmitted | 76 % |
| Total Solar Energy Absorbed | 15 % |
| Shading Coefficient | 0.91 |
| Total Solar Energy Rejected | 20 % |

